

# ARCHCO™ 476P EPOXY

**High Temperature Internal Epoxy Phenolic-Novolac Lining for Tanks and Pipes**  
**100% Solids - Plural Component**

## Description

Archco 476P Epoxy is a two-part, high-temperature resistant, epoxy phenolic-novolac system designed for internal tank linings requiring excellent chemical and temperature resistance over a wide range of temperatures and pressures. It is a 100% solids systems for plural component spray applications.

## Uses

Corrosion protection for steel tanks, vessels, internal and external pipes in a variety of industries. The coating will protect tanks, vessels and piping against crude oil, seawater, wastewater, fuels, solvents, and lubricants up to 275°F (135°C).

## Features

- Excellent adhesion
- Excellent chemical resistance
- High temperature immersion resistance (up to 275°F / 135°C)
- Cathodic disbondment resistance
- Fast cure

## Application

All contaminants shall be removed from the steel surface to be coated. Oil and grease should be removed in accordance to SSPC-SP-1. Surfaces shall be free from projections, sharp edges, high points and fillets must be ground smooth including all corners. Prepare surfaces by grit blasting to a clean near-white finish, SSPC-SP 10, NACE No. 2 or Sa 2-1/2. Appropriate angular grit shall be used to achieve a 3 to 5 mil (76 - 127 microns) anchor profile. Vacuum tank floor to remove grit prior to coating.

To spray Archco 476P Epoxy, a plural-component, airless spray unit with a proportioning pump capable of a volume mixing ratio of 2:1 shall be used. Standard ancillary equipment should include minimum 10 gallon (38 L) hoppers, 2 each static mixers, 25 ft. max x ¼" whip hose (7.5 m max. x 6.25 mm), and mastic gun with a 23 to 31 thou (0.58 - 0.79 mm) tip. Part A should be heated to 100°F-120°F (38°C - 49°C) and Part B should be heated to 90°F-110°F (32°C - 43°C). Hose bundle shall be set at 100°F-120°F (38°C - 49°C).

A wet-on-wet spray technique should be used to achieve a minimum thickness of 20 mils (508 microns) DFT. The coating thickness should be measured using a wet-film thickness gauge. The equipment settings are only guidelines and may vary based on equipment and specific application.



# Archco™ 476P Epoxy

## TECHNICAL DATA

<b>PROPERTIES</b>	<b>PLURAL - VALUE</b>
<b>Solids Content By Volume</b>	100%
<b>Base Component — unmixed @ 77°F (25°C)</b>	
Specific Gravity	1.3
Viscosity	22,000 cP
Color	White
<b>Hardener — unmixed @ 77°F (25°C)</b>	
Specific Gravity	1.2
Viscosity	34,000 cP
Color	Black
<b>Mixed Material — mixed @ 77°F (25°C)</b>	
Specific Gravity	1.3
Viscosity	25,000 cP
Color	Gray
<b>Mixing Ratio (A/B) by Volume</b>	2:1
<b>by Weight</b>	2:1
<b>Cure Times</b>	
Pot Life @ 77°F (25°C)	30 minutes
Pot Life @ 97°F (36°C)	5 minutes
Time to Dry @ 35°F (2°C)	12-16 hours
Time to Dry @ 50°F (10°C)	8-10 hours
Time to Dry @ 77°F (25°C)	2-3 hours
<b>Cure for Immersion (crude oil)</b>	
@ 35°F (2°C)	20 hours
@ 75°F (24°C)	8 hours
<b>Theoretical Coverage</b>	80 ft <sup>2</sup> /20 mils/gallon (2.0 m <sup>2</sup> /508 microns/L)
<b>Thickness per coat</b>	10-40 mils (254-1016 microns)
<b>Holiday Detection — based on min. mil.</b>	100 volts/mil (3,936 V/mm)
<b>Hardness (ASTM D2240-02)</b>	Shore D 85
<b>Recoat Window</b>	36 to 48 hours @ 75°F (24°C)
<b>Adhesion to Steel</b>	3,200 psi (22 MPa)
<b>Application Temperature</b>	35 to 120°F (2 to 49°C)
<b>Service Temperature</b>	35 to 275°F (2 to 135°C)

**NOTE:** Need to scuff the surface before application of the touch up if it is past 48 hours.

**STORAGE:** Minimum 24 months when stored in original containers @ 40°F (4°C) to 105°F (41°C). On job site where temperatures are below 60°F (15.5°C) product should be kept warm to allow for easy transfer into storage hoppers for warming to proper spraying temperatures.

**CLEANING:** Clean equipment with MEK or equivalent solvent cleaner, such as Archco 400E Thinner.

**HEALTH AND SAFETY:** Wear protective clothing and ensure adequate ventilation. Avoid contact with skin and eyes. See Safety Data Sheet for further information.

**PACKAGING:** 15 gallon (57 L) kits.  
Other sizes available upon request.



### DENSO NORTH AMERICA

<b>HOUSTON:</b> 9710 Telge Road, Houston, Texas, U.S.A. 77095 Tel: 281-821-3355 Fax: 281-821-0304	<b>TORONTO:</b> 90 Ironside Crescent, Unit 12, Toronto, Ontario, Canada M1X1M3 Tel: 416-291-3435 Fax: 416-291-0898
------------------------------------------------------------------------------------------------------------------	-----------------------------------------------------------------------------------------------------------------------------------

www.denso.com

*A Member of Winn & Coales International™*

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.