

C-GRID[®] 450

Carbon-Fiber Grid for Strengthening Timber Piles

Description

C-GRID[®] 450 is a high strength carbon-fiber/epoxy grid for structural repairs of timber piles. The C-GRID[®] 450 requires less grout fill leading to a much lighter structure when compared to typical steel reinforced repairs. The composition is carbon-fiber and epoxy resin. The C-GRID[®] 450 geometry is longitudinal and transverse spacing (2.36" x 2.36" / 60 mm x 60 mm).

Features

- Provides double the strength of the original timber pile
- Reduced weight when compared to steel reinforced repairs
- Non-corrosive (no steel to corrode)
- Lightweight and easy to install
- High tensile strength and modulus
- Requires much less grout when compared to steel reinforcement repair
- Requires only 1/4" (6.3 mm) grout cover
- Grid has excellent bond to grout
- Independently tested by Texas A&M University, Department of Civil Engineering, Structural and Materials Testing Laboratory

Installation

The C-GRID[®] 450 shall be unrolled and cut using tin snips or other suitable method. The cut width of C-GRID[®] 450 shall be determined by including enough material to be imbedded within the grout and a 6" (150 mm) overlap along vertical seam. The grid will require a minimum of 1/4" (6.3 mm) grout cover. Locate the C-GRID[®] 450 between the elevations indicated in the specification and drawings. The C-GRID[®] 450 shall be wrapped around the timber pile with a minimum 6" (150 mm) overlap along the vertical seam. Use nylon zip ties, plastic clips or other plastic accessories to secure vertical seam and maintain the position of the grid during the pumping of grout. On long length repairs which require more than one panel of grid, the C-GRID[®] 450 shall be overlapped 6" (150 mm) above or below the first panel of grid. The fiberglass jacket shall be installed around the pile and C-GRID[®] 450.

Please refer to the SeaShield™ Series 400 Engineering Specifications for complete installation guidelines.



C-GRID[®] 450

Property Specifications

PROPERTIES	LONGITUDINAL PROPERTIES	TRANSVERSE PROPERTIES
Individual strand cross-sectional area	0.00321 in. ² (2.07 mm ²)	0.00321 in. ² (2.07 mm ²)
Average number of strands per unit width	5.0 strands/ft (16.6 strands/m)	5.0 strands/ft (16.6 strands/m)
Area of strands per unit width	0.0241 in. ² /ft. (50.9 mm ² /m)	0.0241 in. ² /ft. (50.9 mm ² /m)
Strand tensile strength	830 lbs (3.7 kN)	730 lbs (3.2 kN)
Grid tensile strength per unit width	4565 lbs/ft (66.4 kN/m)	4015 lbs/ft (58.4 kN/m)
Tensile modulus of elasticity	34,000 ksi (234,500 MPa)	34,000 ksi (234,500 MPa)
Elongation at break	0.99% (0.99%)	0.94% (0.94%)

Notes:

1. Centerline-to-centerline spacing between strands is nominal and based on the average number of strands per unit width. Actual spacing may vary by ± 0.10 inch (± 2.5 mm).
2. The longitudinal direction is in the direction of the roll and the transverse direction is across the width of the roll. For example, if a roll of C-GRID[®] 450 is 47.5" (1206 mm) wide the carbon strands in the transverse direction are 47.5" (1206 mm) in length. If a roll of C-GRID[®] 450 is 500 yards long, the longitudinal strands are 500 yards (457 m) in length.
3. Individual strand cross-sectional area is normalized to the cross-sectional area of the fibers in accordance with ACI 440.2R. The actual measured thickness and width are larger and shall not be used for design purposes.
4. Reported tensile strengths are typical or average properties based on testing. Tensile modulus values are based on properties reported by the carbon fiber supplier. C-GRID[®] 450 exhibits linear elastic behavior so failure strains are estimated using Hooke's Law.
5. C-GRID[®] 450, utilized by Denso North America in the SeaShield Series 400 System, is protected under the following US and European Patents: 6,263,629; 5836,715; 6,123,879; 6,454,889; 6,632,309; 0861353; 1094171.



DENSO NORTH AMERICA

HOUSTON:
9710 Telge Road,
Houston, Texas,
U.S.A. 77095
Tel: 281-821-3355
Fax: 281-821-0304

TORONTO:
90 Ironside Crescent,
Unit 12, Toronto,
Ontario, Canada M1X1M3
Tel: 416-291-3435
Fax: 416-291-0898

www.densona.com

A Member of Winn & Coales International

C-GRID is registered trademark of Chomarat North America, LLC.

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.