

Denso® SeaShield™ SplashZone UW Epoxy

Underwater Coating for Steel, Concrete, Wood & Other Surfaces

STEP 1

Prepare the surface by removing all dirt, loose paint, spalling concrete, rotted wood, marine growth and other contaminants by abrasive blasting or high pressure water blasting (not shown). Hand or Power tool cleaning may be used, but of are limited benefit and time consuming.

SURFACE PREPARATION



STEP 2

With wet gloved hands, hand scoop a quantity of Part A and Part B in equal amounts. Mix and knead the components by hand until they make a uniformed green color.

MIX PRODUCTS



STEP 3

Apply by hand, trowl or broad knife. Spread the epoxy smoothly onto the surface in 1/8" to 1/4" (3.12 to 6.25 mm) thin layer with enough pressure to displace water and air bubbles. Smooth out area by hand. If applying on a dry surface in dry air, periodically re-wet hands and tools to keep epoxy from sticking.

APPLY DENSO SEASHIELD SPLASHZONE UW EPOXY



STEP 4

After product has been applied, allow it to cure. See product data sheets on curing times. If using epoxy as a patch or grout (not shown), force the material into the hole or crack and smooth by hand to the thickness needed.

ALLOW PRODUCT TO CURE



Houston OFFICE:
9710 Telge Road,
Houston, Texas 77095

Tel: 281-821-3355
Fax: 281-821-0304

e-mail: info@densona.com
www.densona.com

VER:137.29

*A Member of
Winn & Coales International*